## Raise3D 木質合成フィラメントTDS

## Wood Powder Reinforced Polylactic Acid

| FEATURES   | APPLICATIONS   |
|--|----------------|
| • Environment friendly and biodegradable         | Product models |
| • Low shrinkage, excellent dimensional stability | • Art crafts   |
| • Light weight, look like nature wood            | Adornments     |

| Properties <sup>[1]</sup>    | Test      | Test<br>Condition | S.I.<br>Unit           | S.I.<br>Typical Value <sup>[2]</sup> |                       |  |  |
|------------------------------|-----------|-------------------|------------------------|--------------------------------------|-----------------------|--|--|
|                              | Standard  |                   |                        | Printing                             | Injection<br>Moulding |  |  |
| Physical Properties          |           |                   |                        |                                      |                       |  |  |
| Density                      | ISO 1183  | 23℃               | g/cm <sup>3</sup>      | 1.05                                 |                       |  |  |
| Glass transition Temperature | ISO 11357 | 10℃/min           | $^{\circ}$ C           | 58                                   |                       |  |  |
| Melt Index                   | ISO 1133  | 190℃,2.16kg       | g/10min                | 5.5                                  |                       |  |  |
| Mechanical Properties        |           |                   |                        |                                      |                       |  |  |
| Tensile strength             | ISO 527   | 50mm/min          | MPa                    | 30.6                                 | 45.5                  |  |  |
| Elongation at break          | ISO 527   | 50mm/min          | %                      | 1.5                                  | 4.5                   |  |  |
| Bending Strength             | ISO 178   | 2m/min            | MPa                    | 40.5                                 | 76.2                  |  |  |
| Bending modulus              | ISO 178   | 2m/min            | MPa                    | 1820                                 | 2550                  |  |  |
| Izod Impact, Notched         | ISO 180   | 23℃               | KJ/m <sup>2</sup>      | 4.0                                  | 6.5                   |  |  |
| Thermal Properties           |           |                   |                        |                                      |                       |  |  |
| Heat distortion temperature  | ISO 75    | 0.45MPa           | $^{\circ}\!\mathbb{C}$ | 53                                   |                       |  |  |
| Flammability                 | UL94      | 1.6mm             | Class                  | НВ                                   |                       |  |  |

<sup>[1]</sup> These are typical values of the product's properties, and these values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes.

http://www.bosikj.com Update: 4/14/2017

**NOTICE:** The data contained in this publication are based on our current knowledge and experience. This information may be subject to revision without informing in advance as new knowledge and experience become available. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE ARE EXPRESSLY EXCLUDED.

<sup>[2]</sup> The listed values are maybe different for pigmented material. Printing conditions: Printing temperature=230°C, printing speed=80mm/s, number of shells=2, Nozzle size=0.4mm, and 100% infill. Injection molding processing conditions: Temperature:210°C;Back pressure:0-1MPa; mould temperature: 30-40°C

## **Typical Conditions of Printing**

| Printing Recommendation | Typical Range        |  |
|-------------------------|----------------------|--|
| Extruder Temperature    | 220-240℃             |  |
| Printing Speed          | 30-100mm/s           |  |
| Bed Temperature         | 100-120℃             |  |
| Layer Height            | 0.1-0.2mm            |  |
| Infill                  | As needed up to 100% |  |
| Matters need attention  | General print        |  |

The parameter is just for referential purpose only. In actual processing, the parameter should be adjusted by construction of 3D machine, shape and size of product, and so on.

## SAFETY AND HANDLING CONSIDERATIONS

Material safety data sheets (MSDS) for resins are available from Guangzhou Popbit 3D Technology Co. Ltd. and its subsidiaries. MSDS sheets are provided to help customers satisfy their own handling, safety, disposal needs, and those that may be required by locally applicable health and safety regulations.

The following comments are general and applied only to panels as supplied.

These panels have a very low degree of toxicity under normal conditions of use and should pose no unusual problems from ingestion, eye, or skin contact. However, caution is advised when handling, storing, using, or disposing of these panels. Caution must be used when cutting banding off coil due to

spring-back of material. Always protect eyes with googles; cover nose and mouth with a filter mask when cutting panels. Color change of the product may be caused by UV exposure in general. So it is recommended that storage should keep in dry, cool place and avoid direct sunlight

We encourage customers and potential users of our products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that our products are not used in ways for which they were not intended or tested, our personnel will assist customers in dealing with ecological and product safety considerations. Your sales representative can arrange the proper contacts.

http://www.bosikj.com Update: 4/14/2017